

**VE500.00  
POLYESTER GLOSSY VARNISH**



**FEATURES**

- Excellent high body
- High body and hardness film

DRYING TIME (20 °C, 45-65% RH, 300 g/m <sup>2</sup> )	
Dust Free	20 min
Touch Dry	30 min
Sandability	180 min
Stackable	8 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyester Glossy Varnish	VE500.00	100	100
Polyester Accelerator	VH400	2	2
Polyester Hardener	HE400	2	2

**KEY INFO**  
It is recommended to use in applications where a surface such as glass is desired after polishing.

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). If surface is desired to be colored, ZD820 Gençcolor Wood Stain can be used as recommended in technical data sheets.

**PACKAGING**

25 KG

