

**VP525.00
POLYURETHANE GLOSSY VARNISH**



FEATURES

- Fast drying
- Highly transparent and vivid appearance
- Excellent levelling
- High and permanent gloss
- Scratch and impact resistance

KEY INFO
It can be polishing within 16-20 hours over 25 °C.
It is high gloss and fast drying topcoat.


DRYING TIME (20 °C, 45-65% RH, 100 g/m ²)	
Dust Free	20 - 30 min
Touch Dry	60 - 70 min
Stackable (500 kg/m ²)	16 - 18 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Glossy Varnish	VP525.00	100	100
Polyurethane Hardener	HP125	100	102
Acrylic Thinner	TA500	0 - 5	0 - 5

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ polyurethane, polyester or UV sanding sealer. Surface must be clean and dust free; remove all dirt (dust, wax etc.). If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining. It is recommended to apply only glossy varnish on the first coat and the next coat with pearlescent or 2 or more coat applications.

PACKAGING

3 KG / 12 KG

