

**VP500.00
POLYURETHANE GLOSSY VARNISH**



FEATURES

- High and permanent gloss
- High body

DRYING TIME (20 °C, 45-65% RH, 100 g/m ²)	
Dust Free	20 - 25 min
Touch Dry	80 - 90 min
Stackable (500 kg/m ²)	16 - 17 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Glossy Varnish	VP500.00	100	100
Polyurethane Hardener	HP904	100	102
Polyurethane Thinner	TP100	0 - 5	0 - 6

PACKAGING

3 KG / 12 KG

KEY INFO

It is suitable for multi-coat and repair applications due to high cracking resistant.
It is suitable for application on coated and steel door surfaces.

**ALTERNATIVE HARDENERS & THINNERS
(15-20°C, 55-60% RH)**

Hardener- HP900 : It is recommended for faster drying time.

Dust free: 20 – 25 min.

Touch dry: 70 – 80 min.

Stackable (500 kg/m²): 16 – 17 h.


Stackable (1000 kg/m²): 40 – 44 h.

Thinner - TA500: Preferable for over 25°C.

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ polyurethane, polyester or UV sanding sealer. Surface must be clean and dust free; remove all dirt (dust, wax etc.). If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining. It is recommended to apply only glossy varnish on the first coat and the next coat with pearlescent or 2 or more coat applications.

