

**VP200.00
POLYURETHANE GLOSSY VARNISH**



FEATURES

- High glossy
- Excellent levelling
- High body
- Resistance to pinholes over 35 °C and 65% relative humidity

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)


Dust Free	20 - 30 min
Touch Dry	90 - 100 min
Stackable (500 kg/m ²)	65 - 70 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Glossy Varnish	VP200.00	100	100
Polyurethane Hardener	HP900	50	53
Polyurethane Thinner	TP100	0 - 10	0 - 12

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ polyurethane, polyester or UV sanding sealer. Surface must be clean and dust free; remove all dirt (dust, wax etc.). If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining. It is recommended to apply only glossy varnish on the first coat and the next coat with pearlescent or 2 or more coat applications.

PACKAGING

3 KG / 12 KG

KEY INFO
It is a glossy topcoat polyurethane varnish that can be used different climatic conditions.

