

VP595.XX POLYURETHANE MATT SERIES VARNISH



FEATURES

- Fast drying
- Stackable in a short time
- Scratch resistance
- Homogeneous matt appearance
- Silky touch effect

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)


Dust Free	8 - 10 min
Touch Dry	20 - 25 min
Stackable (500 kg/m ²)	8 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Matt Series Varnish	VP595.XX	100	100
Polyurethane Hardener	HP159	50	53
Polyurethane Thinner	TP100	50	55

GLOSS OPTIONS

- 05 Full Matt
- 15 Matt
- 25 Special Matt (only this option is EN71.3 certified.)
- 45 Silk Matt

APPLICATION METHOD



SURFACE PREPARATION

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ polyurethane, polyester or UV sanding sealer. Surface must be clean and dust free; remove all dirt (dust, wax etc.). If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining.

PACKAGING

10 LT

KEY INFO

It is designed to be used in both high quality and fast production with its ability to be stacked in 10 hours at 22-25 °C. It can be used for heavy -traffic furnitures due to it's high scratch resistance.

