

**VP508.XX  
POLYURETHANE MATT SERIES VARNISH**



**FEATURES**

- High body
- High transparency
- Homogeneous matt appearance
- Silky touch effect
- High scratch resistance

**DRYING TIME (20 °C, 45-65% RH, 100 g/m<sup>2</sup>)**

Dust Free	8 - 10 min
Touch Dry	20 - 25 min
Stackable (500 kg/m <sup>2</sup> )	10 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Matt Series Varnish	VP508.XX	100	100
Polyurethane Hardener	HP129	50	53
Polyurethane Thinner	TP100	40	50

**GLOSS OPTIONS**

- 15 Matt
- 25 Special Matt
- 45 Silk Matt

**APPLICATION METHOD**



**SURFACE PREPARATION**

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ polyurethane, polyester or UV sanding sealer. Surface must be clean and dust free; remove all dirt (dust, wax etc.). If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining.

**PACKAGING**

2.5 LT / 10 LT

**KEY INFO**  
It leaves a transparent, high body and homogeneous film without disrupting the substrate's appearance. It can be used for spray lines and curtain coater with its long pot-life.

