

**VP500.XX  
POLYURETHANE MATT SERIES VARNISH**



**FEATURES**

- Fast drying
- Homogeneous matt appearance
- Easy to repair


DRYING TIME (20 °C, 45-65% RH, 100 g/m <sup>2</sup> )	
Dust Free	15 - 20 min
Touch Dry	30 - 40 min
Stackable (500 kg/m <sup>2</sup> )	11 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Matt Series Varnish	VP500.XX	100	100
Polyurethane Hardener	HP900	25	25
Polyurethane Thinner	TP100	90	100

**GLOSS OPTIONS**

- 05 Full Matt
- 10 Matt
- 20 Special Matt
- 40 Silk Matt

**APPLICATION METHOD**



**SURFACE PREPARATION**

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ polyurethane, polyester or UV sanding sealer. Surface must be clean and dust free; remove all dirt (dust, wax etc.). If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining.

**PACKAGING**

3 KG / 12 KG

**KEY INFO**

It is suitable for multi-coat and repair applications due to high cracking resistant.

It is suitable for application on coated and steel door surfaces which is economical varnish.

