

**BP548.77
POLYURETHANE PRIMER**



FEATURES

- High flexibility
- High hiding power
- Excellent sanding
- Excellent levelling

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	15 - 20 min
Touch Dry	20 - 40 min
Sandability	60 - 90 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP548.77	100	140 - 150
Polyurethane Hardener	HP548	40	45
Polyurethane Thinner	TP100	5 - 10	10 - 20


KEY INFO

It can be used on MDF without barrier coat.

It can be preferred for glossy topcoat application especially when the base coat is not polyester.

It is suitable to apply up to 250 gr/m² for one coat at 20-23 °C (%55 RH).

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

PACKAGING

4 KG / 15 KG

COLOR OPTIONS



1000
White

