

**BP547.77
POLYURETHANE PRIMER**



FEATURES

- Thixotropic, suitable for vertical applications
- High flexibility
- High hiding power on sharp edges
- Excellent sanding

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	15 - 20 min
Touch Dry	25 - 30 min
Sandability	1 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP547.77	100	140 - 150
Polyurethane Hardener	HP548	40	45
Polyurethane Thinner	TP550	10 - 15	20 - 25

KEY INFO

It is thixotropic polyurethane primer.

It is designed for vertical surface and one tick coat applications. It gives perfect results on 3D surfaces, especially on edges through elastic structure and high hiding power.

It is recommended to apply glossy topcoat after at least 24 hours.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

PACKAGING

4 KG / 15 KG

COLOR OPTIONS



1000
White

