

**BP175.77
POLYURETHANE PRIMER**



FEATURES

- Excellent hiding power
- High resistance to cracking
- High elasticity
- High amount of application

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	17 - 23 min
Touch Dry	30 - 35 min
Sandability	100 - 110 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP175.77	100	140 - 150
Polyurethane Hardener	HP175	40	45
Polyurethane Thinner	TP100	15 - 20	20 - 25

COLOR OPTIONS



1000
White

KEY INFO


It is recommended to use on all indoor wooden surfaces in the furniture industry where high hiding power is demanded.

**ALTERNATIVE HARDENERS & THINNERS
(20°C, 45-65% RH)**

Thinner - TN200: It can be used as alternative thinner when faster drying is required.

KO610: It can be added if faster drying is required.
(0,5% by weight is recommended)

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

PACKAGING

4 KG / 15 KG

