


**BP100.77  
POLYURETHANE PRIMER**



**FEATURES**

- Maximum film thickness
- High hiding power
- Excellent levelling
- Manual and mechanical sanding
- High resistance to cracking

**COLOR OPTIONS**



1000  
White



9103  
Black

**DRYING TIME (20 °C, 45-65% RH, 150 g/m<sup>2</sup>)**

Dust Free	10 - 15 min
Touch Dry	25 - 30 min
Sandability	90 - 100 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP100.77	100	140 - 150
Polyurethane Hardener	HP900	33	35
Polyurethane Thinner	TP100	33	40

**KEY INFO**

It provides maximum adherency and hiding power for pinhole problems caused by sanding especially on turning parts and corners of MDF.  
Also it leaves high body and maksimum hiding power.

**ALTERNATIVE HARDENERS & THINNERS  
(20°C, 45-65% RH)**

Hardener: HP904

Pot Life: 4 h - 4 h 30 min.

Sandability: 65 - 70 min.


Hardener: HP903

Pot Life: 4 h 15 min - 4 h 45 min

Sandability: 60 - 65 min.

Thinner - TN200: Recommended for 10 °C and below temperature applications.

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, dust and other foreign materials (oil, silicone, varnish residues, etc.).

**PACKAGING**

4.5 KG / 18 KG

