

**BP531.77  
POLYURETHANE PRIMER**



**FEATURES**

- High elasticity
- High hiding power
- Easy sanding
- Suitable for machine application

**DRYING TIME (20 °C, 45-65% RH, 150 g/m<sup>2</sup>)**

Dust Free	5 min
Touch Dry	25 - 30 min
Sandability	60 - 70 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP531.77	100	140 - 150
Polyurethane Hardener	HP906	40	45
Polyurethane Thinner	TP100	12	20


**KEY INFO**

It is designed for easy use without cracking on CNC treated surfaces.

It can be used on polyurethane foam without barrier coat if the surface is clean.

It can be applied up to 200 gr/m<sup>2</sup> on vertical surfaces and 260 gr/m<sup>2</sup> on horizontal surfaces.

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

**PACKAGING**

15 KG

**COLOR OPTIONS**



1000  
White

