

**BP530.77
POLYURETHANE PRIMER**



FEATURES

- Strong support for the top coat
- Fast drying
- Easy sanding
- High body

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	3 - 5 min
Touch Dry	15 - 20 min
Sandability	50 - 55 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP530.77	100	140 - 150
Polyurethane Hardener	HP904	40	45
Polyurethane Thinner	TP100	10 - 20	25 - 35

KEY INFO

It is suitable to use as an intermediate primer in order to prevent coverage problems. To improve cracking resistance and for longer pot life it is recommended to use with HP906 Polyurethane Hardener on applied CNC surfaces.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, dust and other foreign materials (oil, silicone, varnish residues, etc.).

PACKAGING

15 KG

COLOR OPTIONS



1000
White

