

**BP323.77  
POLYURETHANE PRIMER**



**FEATURES**

- Long pot-life
- Suitable for machine application


**DRYING TIME (20 °C, 45-65% RH, 150 g/m<sup>2</sup>)**

Dust Free	15 min
Touch Dry	30 min
Sandability	80 - 90 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP323.77	100	140 - 150
Polyurethane Hardener	HP900	33	35
Polyurethane Thinner	TP100	30	34

**KEY INFO**  
It is possible to add more thinner than standard polyurethane primers.

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

**PACKAGING**

18 KG

**COLOR OPTIONS**



1000  
White

