

**BP333.77
POLYURETHANE PRIMER**



FEATURES

- Easy sanding
- High filling power

DRYING TIME (20 °C, 45-65% RH, 150 g/m ²)	
Dust Free	10 - 15 min
Touch Dry	20 - 25 min
Sandability	55 - 65 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP333.77	100	140 - 150
Polyurethane Hardener	HP900	33	35
Polyurethane Thinner	TP100	15	25

**ALTERNATIVE HARDENERS & THINNERS
(10-15°C, 60% RH)**

Thinner - TN200: Recommended for 10 °C and below temperature applications.

10-15 °C	HP900	HP904	HP900+ KO610(%0,1)	HP903
Sanding time between coats	75-85 min	65-75 min	55-65 min	55-65 min

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

PACKAGING

4.5 KG (Only white color option) / 18 KG

COLOR OPTIONS



1000 White 1161 Ivory 8144 Brown

* Only white color is EN71.3 certificated.

KEY INFO

It offers to you easy application through various color options. It is recommended to apply maximum 150 gr /m² per coat in applications.

