

**BP133.77
POLYURETHANE PRIMER**



FEATURES

- Easy sanding
- High filling and hiding power
- Thixotropic, suitable for vertical applications
- High resistance to cracking

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	10 - 15 min
Touch Dry	20 - 25 min
Sandability	55 - 65 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP133.77	100	140 - 150
Polyurethane Hardener	HP133	33	35
Polyurethane Thinner	TP100	15 - 20	18 - 23

KEY INFO

It is a fast drying primer that has been formulated carefully in the balance of quality and price performance.

**ALTERNATIVE HARDENERS & THINNERS
(10-15°C, 60% RH)**

Thinner - TN200: It can be used as alternative thinner when faster drying is required.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

PACKAGING

4.5 KG / 18 KG

COLOR OPTIONS



1000
White

