

**BP400.77  
POLYURETHANE PRIMER**



**FEATURES**

- High filling power
- Fast drying
- No tearing and foam problems during application

**DRYING TIME (20 °C, 45-65% RH, 150 g/m<sup>2</sup>)**

Dust Free	15 - 20 min
Touch Dry	30 - 35 min
Sandability	70 - 80 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Primer	BP400.77	100	140 - 150
Polyurethane Hardener	HP400	33	35
Polyurethane Thinner	TP100	10	18

**KEY INFO**  
Especially designed for curtain applications.  
It can be used 270-300 g/m<sup>2</sup> per coat in application.

**APPLICATION METHOD**




**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.).

**PACKAGING**

18 KG

**COLOR OPTIONS**



1000  
White

