

VP900.77 FIRE RETARDANT POLYURETHANE SEALER



FEATURES

- Fire retardant
- High body
- Easy sanding
- Suitable for vertical application
- Used for public areas (theater, library, school, hospital etc.)

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	16 min
Touch Dry	20 - 30 min
Stackable	24 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Fire Retardant Polyurethane Sealer	VP900.77	100	100
Polyurethane Hardener	HP180	50	55

KEY INFO

The product enlarges by volume while in contact with fire.

By spatula residues can be removed from deformed surface and new application can be done after sanding. Certificate of fire retardant will be valid only if fire resistant MDF, VP900.77 Fire Retardant Polyurethane Sealer and VP900.25 Fire Retardant Polyurethane Matt Varnish applied together.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 220-400 grit sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). Excessive surface abrasion may reduce fire retardant property. Ideal application is 3 coats of sealer and one coat of top coat. For higher fire retardancy more coats / quantity can be applied.

PACKAGING

3 KG / 12 KG

