

**VP900.25  
FIRE RETARDANT POLYURETHANE MATT VARNISH**



**FEATURES**

- Fire retardant
- High body
- Homogeneous matt appearance
- Used for public areas (theater, library, school, hospital etc.)

**DRYING TIME (20 °C, 45-65% RH, 150 g/m<sup>2</sup>)**


Dust Free	20 - 25 min
Touch Dry	45 - 60 min
Stackable	min 20 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Fire Retardant Polyurethane Matt Varnish	VP900.25	100	100
Polyurethane Hardener	HP180	50	55

**GLOSS OPTIONS**

- 25 Special Matt

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 220-400 grit sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). Excessive surface abrasion may reduce fire retardant property. Ideal application is 3 coats of sealer and one coat of top coat. For higher fire retardancy more coats / quantity can be applied.

**PACKAGING**

3 KG / 12 KG

**KEY INFO**

The product enlarges by volume while in contact with fire.

By spatula residues can be removed from deformed surface and new application can be done after sanding. Certificate of fire retardant will be valid only if fire resistant MDF, VP900.77 Fire Retardant Polyurethane Sealer and VP900.25 Fire Retardant Polyurethane Matt Varnish applied together.

