

BP900.77
FIRE RETARDANT POLYURETHANE PRIMER PAINT



FEATURES

- Fire retardant
- High hiding power
- Good adhesion
- Easy sanding
- Used for public areas (theater, library, school, hospital etc.)

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	15 - 25 min
Touch Dry	30 - 40 min
Sandability	90 - 110 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Fire Retardant Polyurethane Primer Paint	BP900.77	100	120 - 130
Polyurethane Hardener	HP180	50	55

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 220-400 grit sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). Excessive surface abrasion may reduce fire retardant property. Ideal application is 3 coats of primer and one coat of top coat. For higher fire retardancy more coats / quantity can be applied.

PACKAGING

3 KG / 12 KG

COLOR OPTIONS



1000
White

KEY INFO

The product enlarges by volume while in contact with fire.

By spatula residues can be removed from deformed surface and new application can be done after sanding. Certificate of fire retardant will be valid only if fire resistant MDF, BP900.77 Fire Retardant Polyurethane Primer Paint and BP900.25 Fire Retardant Polyurethane Matt Paint applied together.

