

**BP900.25
FIRE RETARDANT POLYURETHANE MATT PAINT**



FEATURES

- Fire retardant
- High body
- Homogeneous matt appearance
- High hiding power

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)


| | |
|-----------|-------------|
| Dust Free | 20 - 25 min |
| Touch Dry | 45 - 60 min |
| Stackable | min 20 h |

| PRODUCT | CODE | BY WEIGHT (%) | BY VOLUME (%) |
|------------------------------|----------|---------------|---------------|
| Fire Retardant PU Matt Paint | BP900.25 | 100 | 110 - 120 |
| Polyurethane Hardener | HP980 | 50 | 55 |

GLOSS OPTIONS

- 25 Special Matt

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 220-400 grit sandpaper, removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). Excessive surface abrasion may reduce fire retardant property. Ideal application is 3 coats of primer and one coat of top coat. For higher fire retardancy more coats / quantity can be applied.

PACKAGING

3 KG / 12 KG

COLOR OPTIONS



1000
White

KEY INFO

The product enlarges by volume while in contact with fire.

By spatula residues can be removed from deformed surface and new application can be done after sanding. Certificate of fire retardant will be valid only if fire resistant MDF, BP900.77 Fire Retardant Polyurethane Primer Paint and BP900.25 Fire Retardant Polyurethane Matt Paint applied together.

