

VA450.00
ACRYLIC GLOSSY VARNISH



FEATURES

- High yellowing resistance
- High and permanent glossy
- Excellent levelling
- Easy polishing after 24 hours
- Homogeneous film appearance before and after polishing

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)


Dust Free	25 - 35 min
Touch Dry	2.5 - 3 h
Stackable (500 kg/m ²)	24 - 36 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Acrylic Glossy Varnish	VA450.00	100	100
Acrylic Hardener	HA450	50	55
Acrylic Thinner	TA500	50	55

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). For high yellowing resistance, acrylic systems can be used as basecoat.

PACKAGING

3 KG / 12 KG

KEY INFO

It can be applied on pearl, antique and special effect coatings.

Depending on the ambient temperature, it is recommended to apply maximum 3 coats waiting 15-20 minutes between the coats.

