

VA500.00
ACRYLIC GLOSSY VARNISH



FEATURES

- Closed pore application
- Excellent yellowing resistance
- Fast drying

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)


Dust Free	20 - 25 min
Touch Dry	50 - 60 min
Stackable (500 kg/m ²)	36 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Acrylic Glossy Varnish	VA500.00	100	100
Acrylic Hardener	HA190	10	10
Acrylic Thinner	TA500	50	55

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be removed from dust and other foreign materials (oil, silicone, varnish residues, etc.). For high yellowing resistance, acrylic systems can be used as basecoat.

PACKAGING

3 KG / 15 KG

KEY INFO

It can be apply on wood, also pre-tested metal surfaces. The gloss level is around 90 gloss (60°).

It doesn't cause pinhole problems in oven even if applied in high quantity.

