

**VP551.00**  
**POLYACRYLIC GLOSSY VARNISH**



**FEATURES**

- High yellowing resistance
- High body
- High glossy and transparency
- Excellent levelling

**DRYING TIME (20 °C, 45-65% RH, 100 g/m<sup>2</sup>)**


Dust Free	20 - 25 min
Touch Dry	170 - 180 min
Stackable (500 kg/m <sup>2</sup> )	36 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyacrylic Glossy Varnish	VP551.00	100	100
Polyacrylic Hardener	HP551	100	110
Acrylic Thinner	TA500	30 - 50	35 - 55

**GLOSS OPTIONS**

- 00 Glossy

**APPLICATION METHOD**



**SURFACE PREPARATION**

The best performance is achieved to be applied on previously sanded surfaces which are pre-coated with GENÇ Polyurethane, Polyester or UV sealer. Surface must be clean and removed from all dirties. If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining.

**PACKAGING**

12 LT

**KEY INFO**

The film gives glass effect when the floor is very well filled, properly componentized and adapt the specified times between the coats. It has clear appearance like water in package.

