

VP460.00 POLYACRYLIC GLOSSY VARNISH



FEATURES

- Light colored appearance
- High and permanent glossy
- Scratch and impact resistance
- Excellent levelling
- Polishing after 20 hours
- Higher yellowing resistance than polyurethane varnishes
- Suitable for vertical applications

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)


Dust Free	15 - 30 min
Touch Dry	3 - 4 h
Stackable	24 - 36 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyacrylic Glossy Varnish	VP460.00	100	100
Polyacrylic Hardener	HP460	100	110
Acrylic Thinner	TA500	10 - 15	10 - 20

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

The best performance is achieved to be applied on previously sanded surfaces which are precoated with GENÇ Polyurethane, Polyester or UV sealer. Surface must be clean and removed from all dirties. If the topcoat is desired to be colored, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet. PM901 Pearl Paste can be used to obtain required effect as shining.

PACKAGING

24 KG

KEY INFO

Polyacrylic varnish come into prominence which has light colored appearance and thixotropic properties. Apart from the topcoat applications of coated surfaces, it can be used broken white and pastel colors on surface.

