

BA500.XX ACRYLIC MATT SERIES PAINT



FEATURES

- Characteristic excellent esthetic appearance
- High yellowing resistance
- Homogeneous silky touch effect
- Excellent levelling
- High scratch and impact resistance

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)

| | |
|-----------|--------|
| Dust Free | 25 min |
| Touch Dry | 1 h |
| Stackable | 24 h |

| PRODUCT | CODE | BY WEIGHT (%) | BY VOLUME (%) |
|---------------------------|----------|---------------|---------------|
| Acrylic Matt Series Paint | BA500.XX | 100 | 100 |
| Acrylic Hardener | HA190 | 33 | 35 |
| Acrylic Thinner | TA500 | 30 - 40 | 35 - 45 |

GLOSS OPTIONS

- 10 Matt
- 25 Special Matt
- 50 Silk Matt

APPLICATION METHOD



SURFACE PREPARATION

After sanding, the surface must be removed from dust and other foreign materials (oil, silicone, etc.) before application of topcoat. BA500.XX Acrylic Matt Series Paint should be applied to Genç Polyester, Acrylic, PU or UV Cured White Primer lacquered surfaces, preferably sanded with 220-320-400 grit sandpaper respectively.

It is especially recommended to use Genç BE401.77 Polyester Primer or BP548.77 Genç Polyurethane Primer as a basecoat.

PACKAGING

4.5 KG / 18 KG

COLOR OPTIONS



1000
White

KEY INFO

It is absolutely necessary to use in projects that are exposed to high UV rays in which color stabilization is desired to be at maximum level.

Suitable for use in environments with high humidity and heat exchange, such as bathrooms and kitchens.

