

**BE401.77
POLYESTER PRIMER**



FEATURES

- Easy sanding
- High hiding and filling power
- Horizontal and vertical application

DRYING TIME (20 °C, 45-65% RH, 250 g/m ²)	
Dust Free	15 - 20 min
Touch Dry	70 - 90 min
Sandability	4 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyester Primer	BE401.77	100	120 - 130
Polyester Hardener	HE400	2.25	2.5
Polyester Accelerator	VH400	2.25	2.25
Polyester Thinner	TO190	10	12

COLOR OPTIONS



1000
White

KEY INFO

It is designed to protect the paint glossy maximum time on the floor of glossy topcoat paint applications.

It can be sanded very easily even after a long time.

**ALTERNATIVE HARDENERS & THINNERS
(20°C, 60% RH)**

Hardener - HE405: It can be used to increase the gel time duration to 2 hours in manuel applications.

* This time can change depending on the ambient temperature and humidity.

Thinner - TN200, TN160: If TO190 thinner is not available, they can be used as an alternative thinners.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, removed from dust and other foreign materials (oil, silicone etc.)

PACKAGING

10 KG / 20 KG

