

**VN100.XX
CELLULOSIC MATT SERIES VARNISH**



FEATURES

- Good levelling
- Resistance to physical agents
- Scratch resistance
- Fast drying
- Homogeneous matt appearance

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)

Dust Free	8 - 10 min
Touch Dry	20 - 25 min
Stackable	min 8 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Cellulosic Matt Series Varnish	VN100.XX	100	100
Cellulosic Thinner	TN200	100 - 110	120 - 130

GLOSS OPTIONS

- 15 Matt
- 40 Silk Matt

APPLICATION METHOD



SURFACE PREPARATION

To be applied polyurethane or cellulosic basecoat on the surface. The surface can be sanded with 220-280-400 or 280-400 grit sandpaper respectively.

PACKAGING

0.85 KG / 3 KG / 12 KG

KEY INFO

It is recommended for amateur users in applications where fast drying is required on veneers and solid surfaces.

It is suitable for silvery and pearl applications.

Colorful applications can be done with ZD900 Gençmix Varnish Colorant.

