

**BN100.77
CELLULOSIC PRIMER**



FEATURES

- Fast drying
- Easy sanding
- High hiding power
- High filling power

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	10 - 15 min
Touch Dry	15 - 20 min
Sandability	45 - 60 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Cellulosic Primer	BN100.77	100	100
Cellulosic Thinner	TN200	60	70

KEY INFO

It can be preferred as a surface primer in lacquer projects where fast drying and high hiding power is desired. It is recommended to use with Genç K0540 Retarder Additive in high humidity application environments where air humidity is 60% and above.

APPLICATION METHOD



SURFACE PREPARATION

The surface must be removed from oil, rust and bloated paint residues which must be sanded with 180-220 sandpaper before application.

PACKAGING

0.85 KG / 3 KG / 13 KG

COLOR OPTIONS



1000
White



9103
Black

