

BN301.77
CELLULOSIC PRIMER



FEATURES

- Fast drying
- Easy sanding

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	10 - 15 min
Touch Dry	15 - 20 min
Sandability	35 - 40 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Cellulosic Primer	BN301.77	100	120
Cellulosic Thinner	TN200	80 - 100	90 - 110

APPLICATION METHOD




SURFACE PREPARATION

Before application, surface must be removed from dust and other foreign materials (oil, silicone, varnish residues etc.).

PACKAGING

13 KG

COLOR OPTIONS



1000
White



8144
Brown

KEY INFO

It is a fast drying cellulosic primer which has good hiding power.

It is recommended to use with Genç K0540 Retarder Additive in high humidity application environments where air humidity is 60% and above.

