

BN350.77 CELLULOSIC PRIMER



FEATURES

- Fast drying
- Easy sanding

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

| | |
|-------------|-------------|
| Dust Free | 15 - 20 min |
| Touch Dry | 20 - 25 min |
| Sandability | 35 - 45 min |

| PRODUCT | CODE | BY WEIGHT (%) | BY VOLUME (%) |
|--------------------|----------|---------------|---------------|
| Cellulosic Primer | BN350.77 | 100 | 110 - 120 |
| Cellulosic Thinner | TN200 | 70 - 100 | 80 - 120 |

KEY INFO

It is a cellulosic primer that can be used to protect the surface and to provide a smooth surface before the cellulosic paint applications.

APPLICATION METHOD




SURFACE PREPARATION

The surface must be removed from oil, rust and bloated paint residues.

PACKAGING

13 KG / 18 KG

COLOR OPTIONS



1110
White

