

## **VL280.77.0000 EPOXY BARRIER**

Epoxy barrier which is transparent, two component, flexible is developed to isolate oily woods like teak, rosewood. It can be used to provide optimum adhesion on MDF surfaces and isolation in oily woods and to prevent bubbles due to air gap in deep porous coatings. It is recommended to use VL280.77 Epoxy Barrier Varnish in order to use prevent whitening problem that may occur in over time before filling through low penetration feature.

### **EPOXY BARRIER - TECHNICAL SPECIFICATIONS**

<b>PRODUCT</b>	<b>HARDENER</b>	<b>COMP. RATIOS</b>	<b>SOLID CONTENT (%)</b>	<b>VISCOSITY (DIN4, 20°C)</b>	<b>DENSITY (g/cm<sup>3</sup>)</b>	<b>POT LIFE (20°C, sa)</b>	<b>APPLICATION/ COAT (20°C 60-90g/m<sup>2</sup>)</b>	<b>DRYING TIME FOR OVERCOATING (20°C, h)</b>
VL280.77.0000	HP280	100/100	11	12"	0,91	4-6	1	Min.3

