

**VP600.77**  
**POLYURETHANE SEALER**



**FEATURES**


- High transparency
- High wetting and suitable for open pore applications

**DRYING TIME (20 °C, 45-65% RH, 100 g/m<sup>2</sup>)**

Dust Free	10 - 15 min
Touch Dry	35 - 45 min
Sandability	90 min - 100 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Sealer	VP600.77	100	100
Polyurethane Hardener	HP600	50	53
Polyurethane Thinner	TP100	25	30

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, remove dust and other foreign materials (oil, silicone, varnish residues, etc.). If the surface is desired to be colored, it can be stained using ZD820 Gençcolor Wood Stain or BS600 Woodtex Wood Colourant. For coloring the varnish, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet.

**PACKAGING**

3 KG / 12 KG

**KEY INFO**

Transparent sealer developed for open pore applications. Wets perfectly all the pore. Even suitable for teak and rose veneers. Good for fiber rising.

