

**VP610.77  
ULTRA TRANSPARENT POLYURETHANE SEALER**



**FEATURES**


- High transparency
- Resistant to whitening caused by impacts
- Suitable chemical structure for open pore applications

DRYING TIME (20 °C, 45-65% RH, 100 g/m <sup>2</sup> )	
Dust Free	20 - 30 min
Touch Dry	60 - 80 min
Sandability	120 - 150 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Sealer	VP610.77	100	100
Polyurethane Hardener	HP600	50	53
Polyurethane Thinner	TP100	0-10	0-10

**KEY INFO**  
It doesn't cause hazy appearance in the grains by time. Due to its elastic structure, it is resistant to whitening which can be caused by scratches or impacts.

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, remove dust and other foreign materials (oil, silicone, varnish residues, etc). If the surface is desired to be colored, it can be stained using ZD820 Gençcolor Wood Stain or BS600 Woodtex Wood Colourant.

**PACKAGING**

3 KG / 12 KG

