

**VP701.77  
POLYURETHANE SEALER**



**FEATURES**

- High filling power
- Easy sanding
- Easy of application

| DRYING TIME (20 °C, 45-65% RH, 100 g/m <sup>2</sup> ) |             |
|---|-------------|
| Dust Free   | 10 min      |
| Touch Dry   | 20 - 25 min |
| Sandability   | 45 min      |

| PRODUCT               | CODE     | BY WEIGHT (%) | BY VOLUME (%) |
|-----------------------|----------|---------------|---------------|
| Polyurethane Sealer   | VP701.77 | 100           | 100           |
| Polyurethane Hardener | HP903    | 50            | 53            |
| Cellulosic Thinner    | TN200    | 10 - 20       | 10 - 20       |

**KEY INFO**

It has been developed to create high body surfaces in low-quality MDF and massive use applications. It can be used before primer and top coat varnish application.

It is advised to apply maximum two coats for products that have smallest details and mass production. It is suitable for light colored wooden surfaces in multi-coat applications.

**APPLICATION METHOD**



**SURFACE PREPARATION**

Before application, the surface must be sanded with 180-220 sandpaper, remove dust and other foreign materials (oil, silicone, varnish residues, etc.). If the surface is desired to be colored, it can be stained using ZD820 Gençcolor Wood Stain or BS600 Woodtex Wood Colourant. For coloring the varnish, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet.

**PACKAGING**

12 KG / 25 LT

