

**VP700.77
POLYURETHANE SEALER MAXI-FILLER**



FEATURES

- Fast drying
- High filling power
- Easy sanding
- Resistance to flow

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)

Dust Free	5 - 10 min
Touch Dry	18 min
Sandability	50 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Sealer	VP700.77	100	100
Polyurethane Hardener	HP777	33	35
Polyurethane Thinner	TP100	33 - 50	33 - 50

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, remove dust and other foreign materials (oil, silicone, varnish residues, etc). If the surface is desired to be colored, it can be stained using ZD820 Gençcolor Wood Stain or BS600 Woodtex Wood Colourant. For coloring the varnish, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet.

PACKAGING

12 KG

KEY INFO

It has been developed to create high body surfaces in low-quality MDF and massive use applications. It can be used before primer and top coat varnish application.

It is advised to apply maximum two coats for products that have smallest details and mass production.

It is suitable to be used as MDF BARRIER to reduce surface absorption in all MDF types. Especially recommended for chair manufacturers.

