

**VP910.77
POLYURETHANE SEALER FOR EXTERIOR**



FEATURES

- Suitable elastic film structure for exterior
- High filling power

DRYING TIME (20 °C, 45-65% RH, 100 g/m ²)	
Dust Free	10 - 15 min
Touch Dry	25 - 30 min
Sandability	60 - 90 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Sealer	VP910.77	100	100
Polyurethane Hardener	HP920	50	50
Polyurethane Thinner	TP550	20 - 30	20 - 30

KEY INFO

It is a elastic polyurethane sealer with high physical and chemical resistance designed for use as basecoat of exterior wooden surfaces.

It is recommended to use when it is not raining and humidity is below 80%. For the best result apply 2 coats and wait 18 hours before applying VP960.XX.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, remove dust and other foreign materials (oil, silicone, varnish residues, etc). If the surface is desired to be colored, it can be stained using VW240 Water Based Semi-Transparent Primer or BS500 Colored Transparent Wood Primer as the defined in the technical data sheet.

PACKAGING

3 KG / 12 KG

