

**VP680.77
ELECTROSTATIC POLYURETHANE SEALER**



FEATURES


- Suitable for electrostatic applications
- Easy sanding
- High filling power

DRYING TIME (20 °C, 45-65% RH, 100 g/m ²)	
Dust Free	5 min
Touch Dry	7 min
Sandability	45 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Electrostatic Polyurethane Sealer	VP680.77	100	100
Polyurethane Hardener	HP680	50	53
Polyurethane Thinner	TP680	20 - 25	20 - 25

KEY INFO
High quality sanding sealer with thixotropic and electrostatic features which can be used easily in vertical applications.
Covering efficiency is minimum 90%.
For the best result in electrostatic applications must be applied with TP680 thinner.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 sandpaper, remove dust and other foreign materials (oil, silicone, varnish residues, etc). If the surface is desired to be colored, it can be stained using ZD820 Gençcolor Wood Stain or BS600 Woodtex Wood Colourant. For coloring the varnish, ZD900 Gençmix Varnish Colorant can be used as the defined in the technical data sheet.

PACKAGING

12 KG

