

**BP695.00
POLYURETHANE GLOSSY PAINT**



FEATURES

- High film body
- Very high glossy
- Excellent thixotropy on vertical surfaces
- Maximum yellowing resistance
- High hiding power
- Excellent levelling and surface hardness

DRYING TIME (20 °C, 45 - 65% RH, 100 g/m ²)	
Dust Free	20 - 25 min
Touch Dry	4 h
Stackable (500 kg/m ²)	48 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Glossy Paint	BP695.00	100	110 - 120
Polyurethane Hardener	HP695	50	55
Acrylic Thinner	TA550	25 - 30	30 - 35

COLOR OPTIONS



1000
White

KEY INFO

The choice of BE401 Polyester White Primer or BP548 Polyurethane White Primer on the ground will ensure the high gloss and lasting of the topcoat paint.

It is recommended to wait 36 h for maximum polishing efficiency.

**ALTERNATIVE HARDENERS & THINNERS
(10-15 °C, 60% RH)**

Thinner - TA500: It can be preferred in hot and / or humid weather conditions.


Thinner - TP541: It can be added at 2-5% in summer seasons.

Hardener - HP555: It can be used to fast drying.

GLOSS OPTIONS

- 00 Glossy

APPLICATION METHOD



SURFACE PREPARATION

To be applied on Genç Polyurethane, Polyester or UV basecoat which are preferably sanded with 220-280-400 or 220-400 grit sandpaper respectively.

PACKAGING

3 KG / 12 KG

