

**BP101.XX
POLYURETHANE MATT SERIES PAINT**



FEATURES

- Homogeneous matt
- Excellent levelling

DRYING TIME (20 °C, 45-65% RH, 100 g/m²)


Dust Free	10 - 15 min
Touch Dry	45 - 60 min
Stackable (500 kg/m ²)	20 h

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Matt Series Paint	BP101.XX	100	110 - 120
Polyurethane Hardener	HP908	25	30
Polyurethane Thinner	TP100	40	45

GLOSS OPTIONS

- 25 Special Matt
- 50 Silk Matt

APPLICATION METHOD



SURFACE PREPARATION

To be applied on Genç Polyurethane, Polyester or UV Basecoat which are preferably sanded with 220-280-400 or 220-400 grit sandpaper respectively.

PACKAGING

3 KG / 12 KG

COLOR OPTIONS



1000
White

KEY INFO
It can be colored with Genç Cellulosic or Polyurethane pastes.

