

BP700.40 POLYURETHANE PANEL DOOR PAINT

FEATURES

- Good levelling
- Homogeneous matt


DRYING TIME (20°C, 45-65% RH, 100 g/m ²)			
Dust Free	10 - 15 min		
Touch Dry	40 - 50 min		
Stackable (500 kg/m²)	24 h		

KEY INFO

It is compatible with polyurethane and cellulosic color pastes which can be applied on door skinned panel door surfaces. It can be applied up to 180 gr/m^2 for one coat.

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Polyurethane Panel Door Paint	BP700.40	100	110 - 120
Polyurethane Hardener	HP900	25	30
Polyurethane Thinner	TP100	30	35

APPLICATION METHOD



SURFACE PREPARATION

It is recommended to apply on door skinned surfaces and Genç Polyurethane Primer panel doors on sanded surface which are preferably sanded with 220, 400 grit sandpaper.

GLOSS OPTIONS

• 40 Silky Matt

PACKAGING

5 KG / 20 KG

COLOR OPTIONS







