

VA104.77
ACRYLIC SEALER



FEATURES

- High yellowing resistance
- Suitable for bleached, light colored wood
- Easy sanding
- Open/close pore application

DRYING TIME (20 °C, 45-65% RH, 150 g/m ²)	
Dust Free	15 - 20 min
Touch Dry	20 - 30 min
Sandability	90 - 100 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Acrylic Sealer	VA104.77	100	100
Acrylic Hardener	HA190	10	10
Acrylic Thinner	TA500	45	50

KEY INFO
Due to its efficient penetration on pore woods it is ideal for open pore applications. It is suitable for close pore applications with many coats on except oak like deep moire tree. It is an ideal intercoat varnish before high gloss top coat varnish in multicoat applications.

APPLICATION METHOD



SURFACE PREPARATION

Before application, the surface must be sanded with 180-220 grit sandpaper, removed from dust and other foreign materials (oil, silicone, varnish etc.). It is recommended to apply min. 3 coats for close pore applications.

It can be applied as an intermediate coat by adding PM901 metallic and pearl paste.

PACKAGING

3 KG / 15 KG

