

BA 105.77
ACRYLIC PRIMER



FEATURES

- Non-yellowing
- Suitable for open pore applications
- Good hiding power and sandability

DRYING TIME (20 °C, 45-65% RH, 150 g/m²)

Dust Free	15 - 20 min
Touch Dry	40 min
Sandability	min. 90 min

PRODUCT	CODE	BY WEIGHT (%)	BY VOLUME (%)
Acrylic Primer	BA105.77	100	100
Acrylic Hardener	HA190	10	10
Acrylic Thinner	TA500	100 - 110	110 - 120

KEY INFO

Suitable for projects requiring open pore application. It offers both high yellowing resistance and esthetic appearance together.

APPLICATION METHOD



SURFACE PREPARATION

Before application surface should be sanded with 180 - 220 grit sandpaper. Surface must be clean and dust free; removed from all dirties (oil, silicone, varnish residues, etc.).

PACKAGING

15 KG

COLOR OPTIONS



1000
White

