

## VP340 POLYURETHANE SEALER

VP340 is a two component polyurethane sealer which has fast drying and good filling properties.

VP340 Polyurethane Sealer, has been produced and presented to the market provide for maximum transparency and high penetration power product need. The product differs from the other sealers which have been using in market for these reasons explained below.

## **PRODUCT PROPERTIES**

- Maximum transparency
- High penetration power

It can be used for furniture and decoration works for interior use, to protect the applied surface on all types of wooden surfaces such as massive and veneer. It is also provide a smooth surface before the topcoat application. The product can be applied with airmix or conventional spray guns.

DRYING TIME (20°C, 45-65 % RH, 150 g/m²)				
TOUCH DRY	20 - 25 min.			
SANDABILITY	60 - 70 min.			



TECHNICAL SPECIFICATONS OF GENC POLYURETHANE SEALER								
PRODUCT	POLYURETHANE HARDENER	MIXING RATIO	NON VOLATILE MATTER I.COMP (%)	NON VOLATILE MATTER I + 2 COMP (%)	VISCOSITY (KU, 25°C)	DENSITY (g/cm³)	POT LIFE (20°C, h.)	
VP340	HP340	100/50	56 ± 2	44 ± 2	120 - 130	1,10 ± 0,03	4 - 5	
VP350	HP777	100/50	51 ± 2	45 ± 2	85 - 90	1,03 ± 0,03	1 - 1,5	

\* Product can be applied 2-3 coats (150 gr/m<sup>2</sup>, for one coat). According to the weather conditions, should be waiting min. 1,5 hours, max. 4 hours between each coat. If the polyurethane sealer is desired to be colored, Gençmix Varnish Colorant (ZD900) can be used.



## VP340 POLYURETHANE SEALER



COMPARISON TABLE FOR GENÇ POLYURETHANE SEALER					
	VP340	VP350			
Automatic Spray Machine	$\checkmark$	$\checkmark$			
Airmix Spray	$\checkmark$	$\checkmark$			
Conventional Spray	$\checkmark$	$\checkmark$			
Transparency	+++	+			
Penetration Power	++	+			
Filling Power	++	+++			
Sandability	++	+++			

+++: Best ++: Good +: Average